

ACME ANALYTICAL LABORATORIES LTD.

Final Report

Client: Entourage Mining Inc.

File Creator: 7-May-09

Job Number: VAN09001529

Number of: 12

Project: None Given

Shipment ID:

P.O. Number:

Received: 5-May-09

Method	WGHT	G6	1DX	1DX	1DX	1DX	1DX	1DX	1DX
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	
Unit	KG	GM/T	PPM	PPM	PPM	PPM	PPM	PPM	PPM
MDL	0.01	0.01	0.1	0.1	0.1	1	0.1	0.1	0.1
Sample Type									
HOC09 P0C Rock	0.18	8.26	22.9	110.4	1063.6	274	8	19.8	
HOC09 P0C Rock	0.19	23.78	4.5	136.9	1506.7	436	11.6	4.6	
HOC09 P0C Rock	0.29	17.75	49.1	227.5	1679	198	7.4	22.3	
HOC09 P0C Rock	0.23	10.87	14.1	132.5	1414.7	508	3.1	15.9	
HOC09 P0C Rock	0.32	2.16	3	25.3	261.3	54	1	4.6	
HOC09 P0C Rock	0.09	13.61	8.9	94.9	1061.6	161	16.5	8.2	
HOC09 P0C Rock	0.39	1.45	3	26	46.4	66	0.3	8.9	
HOC09 P0C Rock	0.28	17.36	8	64.2	139	58	4.1	29.7	
HOC09 P0C Rock	0.21	1.21	41.2	130.8	1867.3	301	0.6	63.4	
HOC09 P01 Rock	0.46	0.06	0.3	3.4	8.9	9	<0.1	3.3	
HOC09 P01 Rock	0.75	0.01	0.2	3.4	38.6	21	<0.1	4	
HOC09 P01 Rock	0.33	24.97	4.4	80.1	2057.1	41	16.4	15.7	
Pulp Duplicates									
HOC09 P01 Rock	0.33	24.97	4.4	80.1	2057.1	41	16.4	15.7	
HOC09 P01 REP		23.88							
HOC09 P0C Rock	0.09	13.61	8.9	94.9	1061.6	161	16.5	8.2	
HOC09 P0C REP			8.7	91.1	1042.5	153	16.8	7.5	
Reference Materials									
STD OXH55 STD		1.35							
STD DS7 STD			20.6	97.7	63.7	381	0.8	54.7	
STD DS7 STD			19.8	103.4	62	397	0.8	56.6	
BLK BLK		<0.01							
BLK BLK			<0.1	<0.1	<0.1	<1	<0.1	<0.1	
Prep Wash									
G1 Prep Blank	<0.01	<0.01	0.3	2	2.7	44	<0.1	3.8	
G1 Prep Blank	<0.01	<0.01	0.2	1.8	2.3	42	<0.1	3.7	

1DX Co PPM	1DX Mn PPM	1DX Fe %	1DX As PPM	1DX U PPM	1DX Au PPB	1DX Th PPM	1DX Sr PPM	1DX Cd PPM	1DX Sb PPM
0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1
13.1	71	6.32	469	2.7	6871.7	0.4	2	0.2	15
3.7	533	8.3	502.8	3.4	19836.5	0.6	7	0.7	14.4
22.9	267	27.49	2156.9	7.5	17489.5	0.7	4	0.5	4.4
9.8	137	7.85	514.5	3.9	6247.3	0.8	2	0.8	8.9
2.2	30	2.45	137.6	0.7	2074.1	0.4 <1	<0.1		4.8
4.9	81	8.68	789.2	1.9	13255.2	0.2	1	0.6	11.7
9.9	108	4.24	593.3	1.2	1437.9	0.5	1	0.2	0.9
7.1	28	26.52	1285.5	3	31764.8	9.9	4	0.1	2.7
22.8	129	29.14	2398.2	14.1	649.9	7.9	3	0.2	22.6
2.6	97	0.88	11.1	0.1	31.7	0.6	2 <0.1		0.2
2	148	2.22	9.7	0.2	4.1	0.5	2 <0.1		0.1
26.4	177	2.71	203.8	0.7	24587	0.5	5 <0.1		7.2
26.4	177	2.71	203.8	0.7	24587	0.5	5 <0.1		7.2
4.9	81	8.68	789.2	1.9	13255.2	0.2	1	0.6	11.7
5	78	8.44	767.6	2	14265.7	0.2	1	0.7	11.9
9.5	629	2.38	49.9	4.2	69.8	3.6	62	6.1	4.8
9.7	639	2.38	56	4.4	64.9	3.6	63	6.2	5
<0.1	<1	<0.01	<0.5	<0.1	<0.5	<0.1	<1	<0.1	<0.1
4.3	547	1.97	<0.5		1.5	1.4	3	68 <0.1	<0.1
4.3	543	1.94	<0.5		1.3	0.5	2.9	58 <0.1	<0.1

1DX Bi PPM	1DX V PPM	1DX Ca %	1DX P %	1DX La PPM	1DX Cr PPM	1DX Mg %	1DX Ba PPM	1DX Ti %	1DX B PPM	
	0.1	2	0.01	0.001	1	1	0.01	1	0.001	20
	0.3	116	0.01	0.008	1	6	0.01	8	0.001	<20
	1.4	8	<0.01	0.024	3	9	<0.01	39	<0.001	<20
	1.6	365	0.02	0.01	3	5	<0.01	50	<0.001	<20
	1.1	56	<0.01	0.013	6	8	<0.01	8	<0.001	<20
	0.2	25	<0.01	0.006	1	7	<0.01	4	<0.001	<20
	0.2	29	<0.01	0.01	1	9	<0.01	4	<0.001	<20
<0.1		123	<0.01	0.005	3	6	<0.01	18	<0.001	<20
	1	56	<0.01	0.071	23	26	<0.01	32	0.002	<20
	4.9	298	0.01	0.015	3	12	<0.01	36	0.002	<20
<0.1		2	<0.01	0.004	2	9	<0.01	7	<0.001	<20
	1.9	4	<0.01	0.005	<1	9	<0.01	18	<0.001	<20
	0.2	43	<0.01	0.038	4	10	<0.01	14	<0.001	<20
	0.2	43	<0.01	0.038	4	10	<0.01	14	<0.001	<20
	0.2	29	<0.01	0.01	1	9	<0.01	4	<0.001	<20
	0.2	28	<0.01	0.01	1	8	<0.01	4	<0.001	<20
	4.3	81	0.88	0.081	10	207	1.01	427	0.105	43
	4.3	80	0.88	0.075	10	205	1.01	437	0.103	41
<0.1	<2	<0.01	<0.001	<1	<1	<0.01	<1	<0.001	<20	
<0.1		38	0.54	0.075	6	8	0.57	281	0.123	<20
<0.1		38	0.52	0.076	7	9	0.58	260	0.119	<20

1DX Al %	1DX Na %	1DX K %	1DX W PPM	1DX Hg PPM	1DX Sc PPM	1DX Tl PPM	1DX S %	1DX Ga PPM	1DX Se PPM
	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1 0.5
	0.06	0.002	0.02	0.2	0.01	0.3	<0.1	0.24	<1 29.6
	0.09	0.004	0.02	0.1	0.05	0.5	<0.1	<0.05	<1 2.7
	0.05	<0.001	0.02	0.4	0.03	0.3	<0.1	<0.05	1 54.1
	0.09	0.002	0.04	0.2	0.01	0.4	<0.1	<0.05	<1 17.2
	0.05	0.002	0.01	0.2	<0.01	0.2	<0.1	<0.05	<1 6.9
	0.05	0.003	<0.01	0.1	0.01	0.1	<0.1	3.26	<1 13.8
	0.03	0.002	<0.01	0.1	<0.01	0.2	<0.1	<0.05	<1 12.3
	0.39	0.007	0.13	0.5	0.03	1.3	<0.1	<0.05	1 8.5
	0.14	0.002	0.02	0.3	<0.01	1.4	<0.1	<0.05	1 6.1
	0.06	0.003	0.02	<0.1	<0.01	0.6	<0.1	<0.05	<1 <0.5
	0.12	<0.001	<0.01	<0.1	<0.01	1.8	<0.1	<0.05	<1 <0.5
	0.08	0.003	<0.01	0.1	0.33	0.3	<0.1	<0.05	<1 8.2
	0.08	0.003	<0.01	0.1	0.33	0.3	<0.1	<0.05	<1 8.2
	0.05	0.003	<0.01	0.1	0.01	0.1	<0.1	3.26	<1 13.8
	0.05	0.002	<0.01	0.1	<0.01	0.2	<0.1	3.19	<1 14.2
	0.95	0.091	0.49	3.9	0.2	1.9	4.1	0.19	5 3.7
	0.98	0.089	0.49	3.6	0.2	2	4.3	0.19	5 3.3
<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5
	1.12	0.133	0.63	<0.1	<0.01	1.9	0.3	<0.05	5 <0.5
	1.04	0.101	0.58	0.1	<0.01	1.8	0.3	<0.05	5 <0.5